



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>6</sup> :</b> <b>C14C 3/02</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 99/23261</b> <b>(43) International Publication Date:</b> 14 May 1999 (14.05.99)
<b>(21) International Application Number:</b> PCT/EP98/06837 <b>(22) International Filing Date:</b> 28 October 1998 (28.10.98)  <b>(30) Priority Data:</b> 9722806.8 30 October 1997 (30.10.97) GB 9820254.2 18 September 1998 (18.09.98) GB 9821084.2 30 September 1998 (30.09.98) GB  <b>(71) Applicant (for all designated States except US):</b> ALBRIGHT & WILSON UK LIMITED [GB/GB]; 210-222 Hagley Road West, P.O. Box 3, Oldbury, West Midlands B68 0NN (GB).  <b>(72) Inventors; and</b> <b>(75) Inventors/Applicants (for US only):</b> COLLINS, Gareth, Rhys [GB/GB]; 22 Surrey Drive, Kingswinford, Dudley, West Midlands DY6 8HR (GB). JONES, Christopher, Raymond [GB/GB]; 110 Sutherland Road, Cheslyn Hay, Nr Walsall, West Midlands WS6 7BS (GB). TALBOT, Robert, Eric [GB/GB]; 3 Meriden Close, Cannock, Staffordshire WS11 1QG (GB). WILLIAMS, Jane [GB/GB]; 6 Reeves Close, Whetstone, Leicester LE8 6YG (GB). ZAKIKHANI, Mohsen [GB/GB]; 86 Croftdown Road, Harborne, Birmingham B17 8RD (GB).		<b>(74) Agent:</b> SAVIDGE, Roger, Gordon, Madgwick; Albright & Wilson UK Limited, Patents Dept., 210-222 Hagley Road West, P.O. Box 3, Oldbury, West Midlands B68 0NN (GB).  <b>(81) Designated States:</b> AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> TANNING LEATHER  <b>(57) Abstract</b>  Leather is tanned by cross-linking collagen with tris(hydroxymethyl)phosphine or a condensate of a tetrakis(hydroxymethyl)phosphonium salt with an amide or amine in a main tannage or retannage.		

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

## TANNING LEATHER

The present invention relates to a novel process for tanning leather using phosphonium salts. Tanning is a process for the preservation of skins, by which is meant the collagen-containing integuments of vertebrates including mammals (e.g. cows, pigs, deer, goats, sheep, seals, antelope, mink, stoats and camels), fish, (e.g. sharks), reptiles (e.g. snakes, lizards and crocodiles), and birds (e.g. ostrich). Skins comprise a layer of collagen, and tanning entails reacting the collagen with a cross linking, or tanning, agent to cross link reactive sites within the collagen molecule. The product of the cross linking is leather, which is substantially less susceptible than skin to bacterial degradation.

A consequence of the cross linking is an increase in the minimum temperature at which the wet leather tends to shrink. This shrink temperature is often used as an indication of the degree of tanning.

The collagen layer of the skin is separated from fats, connective tissue and other subcutaneous protein, and optionally from the outer keratinous layer, by a combination of chemical and physical steps. The former may include liming, bating, pickling and/or degreasing.

The skin is then subjected to treatment in one or more stages with various tanning agents selected to give the desired end properties.

The main types of tannage are:- vegetable tannage, based on tannin as the active cross linking agent; mineral tannage using various polyvalent metal salts, especially salts of chromium, aluminium, iron, or zirconium; and synthetic tanning agents, referred to as "syntans". Syntans include replacement syntans which are active tanning agents capable of tanning leather when used as the sole tannage and auxiliary syntans which are added to other tannages to modify the character of the leather but which are not in themselves active tanning agents. Syntans include various polymers and copolymers, such as those obtained by

condensing formaldehyde with, for example, phenols and/or aryl sulphonates, and acrylate, methacrylate, acrylamide and/or acrylonitrile homopolymers and copolymers. Formaldehyde itself and dialdehydes such as glutaraldehyde are also used in tanning, usually in combination with other tannages.

For centuries the production of leather was based on the vegetable tannages which produce the characteristic brown colour traditionally associated with leather. One of the first mineral tannages was alum, but currently the most widely used tanning agent is chrome, usually in the form of basic chromium sulphate, which produces a blue grey leather with high shrink temperatures. However mineral tannages in general, and chrome tannages in particular are under pressure on environmental grounds. Syntans are less environmentally harmful than mineral tanning agents but typically give an off white or yellowish leather. Formaldehyde and difunctional aldehydes present a health hazard and are unpleasant to handle. Existing tanning processes cannot readily provide a good quality, pure white leather suitable for use as such or for dyeing, at least using environmentally acceptable and economically viable ingredients.

An object of the invention is to provide an environmentally acceptable tanning process which can produce white leather with high shrink temperatures e.g. above 80 and preferably above 85°. A further object is to produce a leather which is readily dyed, to give clear, light shades.

Tetrakis (hydroxymethyl) phosphonium salts which will be referred to generically herein as THP salts have long been used as fire-retardants for textiles and have been applied to the keratinous (fur) side of skins for this purpose. The salts may be applied directly to the fabric or in the form of precondensates which are water soluble or sparingly water soluble copolymers of THP with organic nitrogen compounds such as urea or an amine. Such copolymers are referred to herein as THP condensates. THP condensates may contain 2 or more phosphorus atoms, so long as the phosphorus compound is water soluble to a concentration of at least 0.5 g/l at 25°C. Such phosphorus compounds contain a total of at least 2 hydroxymethyl groups, usually at least one per phosphorus atom, and preferably at least 2 hydroxymethyl groups per phosphorus atom. The group or groups joining the phosphorus atoms together may be of the formula -R-, -R-O-, -R-O-R-, -R-NH-R or -R-R"-R- where R is an alkylene group of 1 to 4 carbon atoms and R" is the residue formed by removal

of two hydrogen atoms, bonded to nitrogen, from a di or polyamide or an amine or di or polyamine, such as urea, a C<sub>1-20</sub> alkylamine, dicyandiamide, thiourea or guanidine. Such compounds with 2 or more, e.g. 3, hydroxyalkyl groups per phosphorus atom may be made by self condensation of THP salts with a compound of general formula R<sup>n</sup>H<sub>2</sub> such as urea, or a C<sub>1 to 20</sub> alkylamine, e.g. by heating at 40 to 120°C. THP salts have also been known as possible ingredients of tanning liquors for more than thirty six years. US. 2 992 879 referred to THP chloride (THPC) as an unsatisfactory tanning agent on its own, and recommended a combination of THPC and a phenol such as resorcinol speculating that the two react together to form an effective tanning agent when the pH is raised. In fact THP salts do copolymerise with phenols such as resorcinol (see, for example, Textile Research Journal, December 1982, P743). US 3 104 151 describes the use of such THPC phenol copolymers as light pretannages for leather in which the main tannage is vegetable or mineral. GB 2 287 953 describes the use of THP salts as cross linkers in conjunction with melamine formaldehyde or urea formaldehyde prepolymers, in order to form a copolymeric tanning agent in situ in the tanning liquor. EP 0 559 867 describes the use of THP sulphate (THPS) on raw or cured skin prior to tanning e.g. in acid degreasing. EP 0 681 030 describes the use of THPS as a cross linker for casein finishes applied to leather after tanning.

THP salts are stable under acidic conditions in the absence of air or oxidising agents. At pH above 3 and in the absence of oxidising agents they are gradually converted to the parent base, tris(hydroxymethyl)phosphine herein referred to as THP. Conversion is rapid and substantially complete between pH of about 4 and 6. Above pH 7, or in the presence of oxidising agents THP salts or THP are converted to tris(hydroxymethyl)phosphine oxide (THPO), conversion being rapid and substantially complete at pH above about 10, e.g. 12. It has been stated that THPO is an effective tanning agent.

We have now discovered that contrary to statements in the art, THPO is not an effective main tanning agent for leather, and that THP salts are also ineffective as main tannages. However we have found that THP and THP condensates are both highly effective main tanning agents. THP is most effective when formed in situ by first impregnating the leather with a THP salt, in the substantial absence of monomers or prepolymers which react or copolymerise with THP and raising the pH above 4 and preferably above 5. THP provides a particularly effective tanning system, which is ecologically friendly. We have found that THP gives

leather which is especially suitable for dyeing. THP is especially effective in combination with syntans. In the absence of other tanning agents, especially vegetable tannages, mineral tannages, aldehydes and phenols the use of THP, alone or with syntans, and especially resin syntans, results in a particularly white leather.

The invention provides a method of tanning which comprises reacting collagen with THP or a THP condensate in a main tannage or retannage.


According to a preferred embodiment this invention provides a method of tanning in which skins which have been subjected to partial tanning in a pretanning operation are contacted with a THP salt in the substantial absence of a monomer or prepolymer capable of reacting or copolymerising therewith or of an oxidising agent capable of oxidising THP to THPO and at a pH below 4, and the pH is raised above 4, preferably above 4.5, more preferably above 5, most preferably above 5.5 e.g. 4 to 7 to form THP but not sufficiently to convert more than 20% of the weight of THP into THPO and for a sufficient time to raise the shrink temperature above 80° and preferably above 85°. According to a preferred embodiment the leather is subsequently retanned and dyed by contacting with a solution or dispersion of an appropriate dye.

According to a further embodiment our invention provides a method of tanning leather in which skins are contacted either simultaneously or consecutively, in one or more stages and in any order, with:-

- (A) THP in the substantial absence of a monomer or prepolymer capable of copolymerising therewith, and/or a THP condensate; and
- (B) a syntan, preferably a resin syntan.

In a preferred embodiment skins are tanned in a process involving an optional pretannage comprising THP, a THP condensate and/or a syntan, a main tannage in which the shrink temperature is raised above 80°C and preferably above 85°C and optionally a retannage wherein (A) THP and/or a THP condensate, and (B) a resin syntan are each used in at least one of the main tannage and the retannage.

For the purpose of this specification "syntan" is used to refer to synthetic organic compounds capable of reacting with collagen to form cross links or to modify the physical properties of the leather and also to auxiliary syntans which do not in themselves contribute substantially to the cross linking but which modify the physical properties of the leather. For example the term includes any water soluble polymer prepared by copolymerising formaldehyde, which is capable of increasing the shrink resistance of collagen and which comprises at least two units of the formula



where each M is an aryl group such as a phenyl, naphthyl or aniline group substituted with one or more hydroxyl and/or sulphate, sulphone or sulphonimide groups or a urea or melamine residue. As used herein the term "syntan" also includes resin syntans which are homopolymers and copolymers of unsaturated carboxylic acids or their salts, esters, amides or nitriles, e.g. acrylic acid, methacrylic acid, acrylamide, acrylonitrile, maleic acid, fumaric acid, itaconic acid, aconitic acid, crotonic acid, isocrotonic acid, citraconic acid, mesaconic acid, angelic acid, tiglic acid and cinnamic acid. The copolymers may also comprise other vinylic comonomers such as styrene. Also included are acetone condensates with, for example sulphones and sulphonamides. Resin syntan may modify such properties as dye levelling, filling, grain appearance, break, grain strength, buffing nap, softness and tensile or tear strength.

THP may be formed in situ from any THP salt by raising the pH. It is preferred to use a catalyst for the formation of THP. For example a mixture of magnesium salt such as magnesium sulphate with a water soluble carboxylate salt such as sodium formate, sodium acetate, potassium propionate or other water soluble alkali metal or ammonium salt of a carboxylic acid, preferably the pH is raised above 3.5, more preferably above 4, e.g. above 4.5. High pH is preferably avoided because it converts THP to THPO, which is substantially ineffective as a tanning agent. We prefer that THP solutions for use according to our invention should have a pH less than 10, more preferably less than 9, especially less than 8, typically less than 7.5, most preferably 4.5 to 7. We prefer that the THP contains less than 15%, more preferably less than 10%, e.g. less than 9% of THPO based on the weight thereof. Generally the less THPO present the better.

The THP salt is preferably the sulphate (THPS), but may also be the chloride (THPC) or phosphate (THPP). Other salts which could less preferably be used include the bromide, sulphite, carbonate, acetate, citrate, formate lactate or borate. In principal, any water soluble THP salt with an anion which does not interact adversely with the leather may be used. It is preferred that oxidising agents for THP should be substantially absent.

The THP condensate may preferably be a condensate of a THP salt and urea or THP salt with an alkyl amine, e.g. a C<sub>1-20</sub> alkylamine. Alternatively the THP salt may be condensed with thiourea, guanidine, ammonia, dicyandiamide or with a combination of comonomers. The THP salt is usually THPC or THPS, although any salt of a counterion which does not react adversely with other components of the system may be used. The THP condensate may be formed in situ by adding THP or a THP salt and e.g. guanidine or dicyandiamide to the tannage.

The THP salt, THP and THP condensate is preferably used in a total concentration of from 0.01 to 20% by weight based on the total weight of the tanning liquor, more preferably 0.5 to 10%, e.g. 1 to 5%, most preferably 1.5 to 4%. The total proportion of the THP salt used is preferably from 0.3 to 20% by weight based on the weight of wet skin, more preferably 1 to 15%, especially 1.5 to 10%, most preferably 2 to 5%.

In the preferred embodiment, we prefer that the THP or THP condensate tanned leather, optionally after one or more other tanning stages, is contacted with an acid, basic or direct dye. It is observed that the rate of uptake of dye from the dyebath is substantially increased in leather which has been tanned using THP or THP condensate.

When the THP or THP condensate is used in combination with a syntan, the latter is preferably a polyacrylate, polymethacrylate, or copolymer of acrylic and/or methacrylic acid with acrylonitrile and/or acrylamide. Typically the polymer has a molecular weight in the range 1,000 to 200,000, more usually 3,000 to 100,000. Alternatively the syntan may be or may comprise a copolymer of formaldehyde with a hydroxy substituted and/or sulphonated benzene, alkyl benzene, naphthalene or alkyl naphthalene such as for example, phenol, benzene sulphonic acid, cresol, toluene sulphonic acid, xylenol, naphthalene sulphonic acid, resorcinol or phenol sulphonic acid, or mixtures, thereof in the form of random or block



copolymers.

The syntan is preferably present at a concentration of from 0.5 to 35% by weight of the tanning liquor. e.g. 1 to 20%, more preferably 2 to 10% especially 3 to 6%. The total proportion of syntan used is preferably from 1 to 20% by weight based on the wet weight of skins, e.g. 2 to 10% especially 3 to 5%.

The proportion by weight of total THP, THP salt and THP condensate to syntan may typically be from 1:10 to 10:1, preferably 1:5 to 2:1, especially 1:2 to 1:1. The total proportion of tannages used is preferably from 2 to 20% active weight based on the wet weight of skins, e.g. 3 to 10%, especially 4 to 8%. The total tannage used preferably comprises more than 80% by weight, more preferably more than 90% by weight, e.g. more than 95% of total THP, THP salts, THP condensate and syntan. Where white leather is required, we prefer that the total tannages consist essentially of THP and/or THP condensate, and syntan. In particular we prefer the leather is not tanned with vegetable or mineral tannage, with aldehydes or with phenols.

The THP is applied in the substantial absence of monomers or prepolymers capable of copolymerising with THP such as phenol, urea, melamine or their precondensates with formaldehyde. For the purposes of this specification, "the substantial absence of monomers or prepolymers" means less than the minimum that would be capable of reacting or copolymerising with 50% of the THP, more preferably less than the minimum that would be required to react or copolymerise with 20%, e.g. less than 5% by weight based on the THP salt, most preferably less than 2%, especially less than 1%.

The THP or THP condensate is preferably applied as a first tanning step with a syntan as a retan. Preferably the THP is applied to acidified skins following aqueous degreasing. E.g. the initial pH is typically below 5, e.g. below 4. We prefer that the pH be raised above 5 and preferably maintained above 6 for the main duration of the tanning process.

The skins are preferably agitated in the tanning liquor for a sufficient time to raise the shrink temperature above 75°C, more preferably above 80°C, most preferably above 85°C.

The tanned skins are typically washed with warm water and fat liquored using a suitable oil or blend of oils. Fat liquoring is normally carried out after dyeing.

Penetration of the hide depends on the thickness of the hide and the pH at which the THP is applied. If the pH of the hide is too low when it is contacted with the THP inadequate take-up of the shrink inhibitor may occur. If the hide is too thick, penetration may be limited to the outer layers of the leather, leaving untreated areas in the interior. The extent to which THP has been absorbed by, and has penetrated, the hide needs to be determined.

THP users may also wish to be able to check effluents to ensure that THP has been removed or reduced to acceptable levels prior to discharge. Hitherto the only way of determining the presence of THP has been to take samples and to send them to an analytical laboratory for detailed analysis. This is a lengthy operation. Since many customers do not have suitably equipped laboratories the results may take days to obtain. Such methods are obviously unsuitable for routine quality control, and cannot provide the rapid feedback required for process control.

Unfortunately, we have found that THP does not readily give characteristic colour responses to any of the reagents most commonly used for the colorimetric analysis of organic bases.

We have now discovered that selenium provides a distinctive bright orange colouration with THP. The selenium is preferably added in the form of an aqueous solution of a colourless, water soluble, inorganic selenium compound and most preferably an oxyacid such selenic or preferable selenous acid or an oxysalt of selenium such as a selenate or preferably a selenite. The salt is preferably an alkali metal or ammonium salt, and most preferably sodium selenite. However, any colourless salt of selenous acid which is sufficiently soluble may be used.

Our invention therefore further provides a method of testing a leather to which THP has been applied as a main tannage or retannage or an effluent from such an operation in order to detect the presence of THP which comprises applying a colourless water soluble inorganic selenium compound such as selenous acid or its salts thereto.

Preferably the concentration of selenium compound in the indicator solution is from 0.005 to 20% especially 0.01 to 10% more especially 0.05 to 5% e.g. 0.07 to 1%.

The indicator is preferably added to hides by steeping, injection, spraying, painting or, most conveniently, application with a dropper. The indicator is preferably used in proportion of from 0.001 to 0.05g e.g. 0.005 to 0.01g per cm<sup>2</sup> of surface.

In aqueous samples the indicator compound is preferably added in a concentration of from 10 to 10000 ppm based on the sample, e.g. 100 to 5000ppm especially 500 to 2000 ppm.

The indicator solution is preferably aqueous and may have an acid, alkaline or neutral pH. For example the solution may be strongly acidified with mineral acid such as sulphuric, hydrochloric or nitric. One convenient form of indicator is an analytical standard comprising 1gm per litre selenium as selenous acid in molar nitric acid.

Alternatively, the indicator may be a neutral or alkaline solution comprising a salt of selenous acid such as sodium selenite. In general the colour develops most strongly in samples having a pH greater than 3.

The dye is characterised spectrophotometrically by an absorption peak at 300 nm.

The invention is illustrated by the following examples in which all percentages are by weight based on the wet weight of skins unless stated to the contrary:-

#### **Example 1**

Degreased sheepskins were placed in a rotating drum with 80% water and 8% sodium chloride for 15 minutes. The pH was 3.4. To the drum was added 10% of a solution containing 25% by weight based on the weight of said solution of THPS. After 60 minutes the pH of the liquor was raised slowly to 6.5 and tanning continued for a further 2 hours. The shrink temperature of the partly tanned leather was measured at 86°C. 4% of a phenol formaldehyde polymer, for example products sold under the "ELTESOL" or "NEOSYN" CPP 48 Registered Trade Marks, which are a white, light-fast syntan was then added to the leather. After a further 60 minutes, the leather was washed with 200% warm (55°C) water for 15 minutes and drained. The wash cycle was repeated.

The washed leather was fat liquored with a sulphated oil sold under the Registered Trade Mark "REMSYNOL" ESA and a sulphited fish oil under the Registered Trade Mark "REMSYNOL" ESI. The pH was adjusted to 3.6 with formic acid and the leather horsed until dry.

The leather was assessed as exceptionally full with a mellow handle, fully light-fast and with high tensile and tear strengths and high shrink temperature:-

Tensile strength (1.4mm) 180Kg cm<sup>-2</sup> in perpendicular and parallel directions

Banmann tear strength (1.4mm) 12 Kg

Final shrink temperature = 92°C

### Example 2

Degreased skins were subjected to the following sequences:-

- (i) 10 mins rotation at pH = 5.2 with 5% magnesium sulphate and 2% sodium acetate and 100% water.
- (ii) Addition of 1% of a 2:1 THPC/urea precondensate available from Albright & Wilson UK Limited under its registered Trade Mark "PROBAN" CC followed by 90 mins rotation at pH = 4.5. The shrink temperature was elevated to 59°C. Testing a sample with selenium indicator gave a pale orange colour evenly distributed through the sample indicating even penetration.
- (iii) The pH was raised to 5.8 by addition of 1% sodium carbonate and the shrink temperature rose to 71°C. The selenium indicator gave a bright orange colouration evenly distributed through the sample.
- (iv) The pH was raised to 6.8 by addition of 0.75% sodium carbonate to give a shrink temperature of 84°C. The leather was tight with no visible case hardening.

No further elevation of shrinkage temperature could be obtained on addition of more carbonate.

### **Example 3**

THP condensate was used to enhance tanning by THP.

The process of Example 1 was repeated using 1% of a 75% aqueous solution of THPS in place of THP condensate in stage (ii) as a control. The maximum shrink temperature obtained was 80-81°C. The process was repeated, but using a mixture of 1% of a THP condensate comprising 3:1 THPC and urea reacted with a C<sub>16-18</sub> amine, and 1% of 75% THPS as the addition in stage (ii). The THP condensate is available from Albright & Wilson UK Limited under its registered Trade Mark "PROBAN" ST. The leather had a shrink temperature of 85°C and a full, tight feel.

### **Example 4**

Example 1 was repeated using in step (ii) a mixture of 0.5% of the THP condensate of Example 1 and 0.5% of the THP condensate of Example 2. The shrink temperature was 74°C.

### **Example 5**

Following treatment with magnesium sulphate and sodium acetate as in stage (i) of Example 1, the skins were rotated for 2 hours with a mixture of 1% of the THP condensate of Example 1 and 1% of a 75% aqueous solution of THPS. The pH fell to 2.9, selenium indicator showed very pale yellow on flesh side only indicating poor penetration. Shrink temperature was 58°C. On basification with sodium carbonate to pH 6.5 the shrink temperature rose to 83°C. Selenium indicator gave an evenly distributed bright orange colour. The leather was of high quality, full and with a tight feel.

### **Example 6**

Example 4 was repeated replacing the THP condensate of Example 1 with that of Example 2. A similar product was obtained at pH 6.5 with a shrink temperature of 84°C.

**Example 7**

Wet blue sheepskins were retanned as follows:-

Wash

200% Water @ 35°C

10'

Drain

Repeat

100 Water @ 35°C

5% "ALBRITE" AD

45'

1.5% Ammonium Bicarbonate

0.5% Sodium Formate

40'

pH 5.6 (through cross section)

Wash

200% Water @ 50°C

10'

Drain

Repeat

100% Water @ 50°C

2% Dyestuff

40'

6% "REMSYNOL" ESA

4% "REMSYNOL" ESI

40'

Adjust pH to 3.4 with formic acid

Horse up

Dry and finish

"ALBRITE" and "REMSYNOL" are registered trademarks

"ALBRITE" AD is an aqueous solution of THP sulphate

**Example 8**

Wet salted sheepskins were treated as follows:-

All floats were approximately 500% :

1st scour

Water @ 35°C

1g/l Wetting agent

0.5g/l Sodium Carbonate

30'

Drain

Flesh

Water @ 35°C

1g/l Wetting agent

2g/l Bating agent

0.5g/l Sodium Metabisulphate

60'

Drain

Wash

Drain

Hydro

Shear wool to required length

Pickle

Water @ 20°C

50g/l Salt

10'

2.5g/l Formic Acid

0.7g/l Sulphuric Acid

120'

Leave overnight with intermittent running pH 2.8-3.0

Add 12g/l "ALBRITE" AD

10'

4g/l Sulphited oil (electrolyte stable)

360'

Leave overnight

Check shrinkage temp  
Basify to pH 6.5 with additions of sod carbonate  
Check shrinkage temp  
Drain  
Rinse horse  
Crust out  
Butt and stake

**Example 9**

Line split English 26K Ox hides were tanned as follows :

Wash

200% Water @ 30°C

10'

Drain

Repeat

200% Water @ 35°C

2% Ammonium Chloride

0.5% Sodium Metabisulphate

60'

pH 8.3 (through cross section)

1% "PANCREOL" PBW1 (Pancreatic bate)

45'

Drain

Wash

200% Water @ 20°C

10'

Drain

Repeat

80% Water @ 20°C Salt

8% Salt

10'

"PANCREOL" is a registered trademark



6°Bé

1.2% Sulphuric Acid

0.4% Formic

3 hours

6°Bé

2.8 pH

Add

10 "ALBRITE" AD

2 hours

Complete penetration

ADD

1.5% Sodium Carbonate

60'

1.5% Sodium Carbonate

60'

pH 6.8

Run for a further 3 hours

T<sub>s</sub> °C 89°C

Horse up

Samm

Shave

Wash

200% Water @ 50°C

10'

Drain

Repeat

100% Water @ 50°C

5% "NEOSYN" AC4 (acrylic resin)

40'

2% Dyestuff

40'

"NEOSYN" is a registered trademark

6% "REMSYNOL" ESA

4% "REMSYNOL" ESI

40'

Adjust pH to 3.6 with formic acid

#### **Example 10**

Leather was produced by the method Example 9 except that retannage and dyeing were as follows:-

150% Water @ 45°C

5% Mimosa

4% "NEOSYN" RW

45'

4% Dyestuff

45'

4% "REMSYNOL" ESA

4% "REMSYNOL" ESI

40'

Adjust pH to 3.4 with formic acid

#### **Example 11**

English degreased pickled sheepskins were tanned as follows:-

80% Water

8% Salt

15 minutes

pH 3.4

6°Bé

10% "ALBRITE" AD

60 minutes

Raise pH slowly to 6.5

120 minutes

Run 120 minutes @ 6.5

Shrinkage temperature 86°C

Retan

ADD

4% "NEOSYN" CPP48 (white, light fast syntan)

60'

Wash

200% Water @ 55°C

15'

Drain

Repeat

100% Water @ 55°C

6% "REMSYNOL" ESI

4% "REMSYNOL" ESA

4% White Pigment

45'

Adjust pH to 3.6 with formic acid

Horse up overnight

Dry

### Example 12

English degreased pickled sheepskins were tanned as follows:-

80% Water

8% Salt

15 minutes

pH 3.4

6°Bé

3.1 "ALBRITE AD75M"

60 minutes

Raise pH slowly to 6.5

120 minutes

Run 120 minutes @ 6.5

Shrinkage temperature 84°C

Retan

"ALBRITE AD75M" is an aqueous solution of THP sulphate

ADD 4% "DEHSCOFIX" 914

Wash

200% Water @ 55°C

15'

Drain

Repeat

100% Water @ 55°C

5% "REMSYNOL" ESI

5% "REMSYNOL" ESA

45'

Adjust pH to 3.4 with formic acid

Horse up overnight

Dry

### **Example 13**

English degreased pickled sheepskins were tanned as follows:-

80% Water

8% Salt

15 minutes

pH 3.4

6°Bé

3% "ALBRITE AD75M"

60 minutes

Raise pH slowly to 6.5

Run 120 minutes @ 6.5

Shrinkage temperature 84°C

Retan

ADD 4% "NEOSYN" DSF2

60'

Wash

200% Water @ 55°C

Drain

"DEHSCOFIX" is a registered trademark

Repeat

100% Water @ 55°C

5% "REMSYNOL" ESI

5% "REMSYNOL" ESA

45'

Adjust pH to 3.6 with formic acid

Horse up overnight

Dry

### CLAIMS

1. A method of tanning which comprises reacting collagen with THP or a THP condensate in a main tannage or retannage.
2. A method of tanning according to claim 1 in which skins which have been subjected to partial tanning in a pretanning operation are contacted with a THP salt in the substantial absence of a monomer or prepolymer capable of reacting or copolymerising therewith or of an oxidising agent capable of oxidising THP to THPO and at a pH below 5, and the pH is raised sufficiently to form THP but not sufficiently to convert more than 20% of the weight of THP into THPO and for a sufficient time to raise the shrink temperature above 80° and preferably above 85°.
3. A method of tanning according to either of claims 1 and 2 in which skins are contacted either simultaneously or consecutively, in one or more stages and in any order, with:-
  - (A) THP in the substantial absence of a monomer or prepolymer capable of copolymerising therewith, and/or a THP condensate; and
  - (B) a syntan.
4. A method of tanning according to any foregoing claim wherein skins are tanned in a process involving an optional pretannage comprising THP, a THP condensate and/or a syntan, a main tannage in which the shrink temperature is raised above 80°C and preferably above 85°C and optionally a retannage wherein (A) THP and/or a THP condensate, and (B) a resin syntan are each used in at least one of the main tannage and the retannage.

5. A method according to any foregoing claim wherein the leather is subsequently dyed by contacting with a solution or dispersion of an appropriate dye.
6. A method according to claim 5 wherein the leather is contacted with an acid, basic or direct dye.
7. A method according to any of claims 3 to 5 wherein the syntan is a resin syntan.
8. A method according to any of claims 2 to 6 wherein tannage comprises a catalyst for the formation of THP.
9. A method according to any foregoing claim wherein the THP and THP condensates are used in a total concentration based on the wet weight of the skins of from 0.3 to 20%.
10. A method according to any foregoing claim wherein a syntan is used in proportion of from 1 to 20% based on the wt weight of the skins.
11. A method according any foregoing claim wherein the proportion by weight of THP to syntan is from 1:10 to 10:1.
12. A method according to any foregoing claim wherein the total proportion of tannage is from 2 to 20% active weight based on the wet weight of the skins.
13. A method according to any foregoing claim wherein the THP and/or THP condensate and syntan comprise more than 90% of the total active weight of tannage.
14. A method according to any foregoing claim wherein the main tannage consists essentially of THP or a THP condensate and the retannage consists essentially of a syntan.

15. A method according to any foregoing claim wherein the penetration of THP into the hides is tested by applying to a sample a solution of selenous acid or a water soluble selenite.



# INTERNATIONAL SEARCH REPORT

International Application No.  
PCT/EP 98/06837

**A. CLASSIFICATION OF SUBJECT MATTER**  
IPC 6 C14C3/02

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)  
IPC 6 C14C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P, X	GB 2 314 342 A (CIBA GEIGY AG) 24 December 1997 see page 1, paragraph 7 - page 7, paragraph 2 see examples 1,2,5,6 see claims 14-17 ---	1,3,7,9, 11
P, X	EP 0 808 908 A (SUEDLEDER GMBH & CO) 26 November 1997 see page 2, line 3 - page 4, line 50 see example 1 ---	1,2,9,10
A	US 3 104 151 A (WINDUS WALLACE ET AL) 17 September 1963 cited in the application see column 1, line 23 - column 2, line 51 see examples 1,14 see claim 10 --- -/--	1,9

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

\* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance  
"E" earlier document but published on or after the international filing date  
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)  
"O" document referring to an oral disclosure, use, exhibition or other means  
"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention  
"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone  
"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.  
"&" document member of the same patent family

Date of the actual completion of the international search

15 February 1999

Date of mailing of the international search report

25/02/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax: (+31-70) 340-3016

Authorized officer

Neugebauer, U

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 98/06837

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No
A	<p>GB 2 287 953 A (BLC THE LEATHER TECHNOLOGY CEN) 4 October 1995  cited in the application  see page 4, paragraph 4 - page 8,  paragraph 3  see example 4</p> <p>-----</p>	1,3

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 98/06837

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
GB 2314342 A	24-12-1997	AU 2491797 A DE 19724468 A NZ 328079 A	08-01-1998 18-12-1997 28-10-1998
EP 0808908 A	26-11-1997	DE 19621219 A	27-11-1997
US 3104151 A	17-09-1963	NONE	
GB 2287953 A	04-10-1995	NONE	

**THIS PAGE BLANK (USPTO)**